



60 mil FiberTite-XT

Product Data

Seaman Corporation's 8155 FiberTite-XT membrane features an 18 x 18 / 1,100 x 1,300 denier weft reinforced polyester knit fabric, coated with a proprietary compound, utilizing DuPont's™ Elvaloy® Ketone Ethylen Ester (KEE) compound as the principle polymer in the hybrid vinyl alloy coating.

DESCRIPTION

8155 FiberTite-XT is a 55-oz sq. yd/nominal 60-mil (1.5 mm) thick membrane and is an Xtra-Tough and Xtra-Thick version of the FiberTite family of membranes. 8155 FiberTite-XT far exceeds all requirements enumerated in ASTM D6754-15 Standard Specification for Ketone Ethylene Ester (KEE) Based Sheet Roofing and has unmatched performance vs. 100 mil competitive products. 8155 FiberTite-XT is a specialty membrane manufactured upon request.

Seaman Corporation is vertically integrated, which allows complete control over the manufacturing process from the selection of the yarns, to the engineering, knitting and weaving of the base fabrics to the final coating process. Today, FiberTite Roofing Membranes are the result of Seaman Corporation's 60 years of applied fabric engineering and coating technology.

All FiberTite Roofing Membranes are constructed using high tenacity/heavy weight yarns to create a base fabric reinforcement to impart superior puncture, tensile and tear resistance properties. The base polyester fabrics are primed with a unique and proprietary adhesive coat that lays the foundation to physically bond the KEE coatings to the "fiber" to maximize seam strength and overall membrane performance.

8155 FiberTite-XT is coated face and back with Seaman Corporation's original "KEE" formulation to provide superior hot air welding characteristics, extreme UV resistance, broad chemical resistance and long-term flexibility and reparability for the installed roofing membrane system. Additionally, 8155 FiberTite-XT exhibits superior tear, puncture, fungus, algae and flame resistance that make FiberTite Roofing Systems some of the most sustainable roofing systems available.

8155 FiberTite-XT membrane is manufactured in conventional and 74-in wide by 75-ft roll goods. Field seaming of the membrane is accomplished by fusing the thermoplastic membrane with conventional hot air welding equipment.

PHYSICAL PROPERTIES

| ASTM D6754-15 | Minimum Requirements | 8155 Typical |
|--|----------------------|-------------------|
| Thickness, mm (in.) ASTM D 751 | 0.81 (0.032) | 1.52 (0.060 nom.) |
| Thickness over Fiber, mm (in) Optical method (inches) | 0.18 (0.007) | .38 (> 0.015) |
| Breaking Strength, N (lbf) ASTM D 751 proc. B - strip | 1499 (338) | 1779 (400) |
| Elongation at Break, % ASTM D 751 - strip | 18 | 18 |
| Tear Strength, N (lbf) ASTM D 751 Proc. B. Tongue Tear | 338 (76) | 556 (125) |
| Linear Dimensional Change ASTM D 1204 max (%) | 1.3 | .78 |
| Fabric Adhesion, N/m (lbf/in) ASTM D 751 | 3330 (19) | no peel |
| Retention of Properties after Heat Aging ASTM D 3045 - 176°/56 days Breaking Strength, strip, % original Elongation at Break, strip, % original | 90 90 | 90 90 |
| Low Temperature Bend after Heat Aging | -30 | -40 |
| Low Temperature Bend ASTM D 2136 (°f) | -30 | -40 |
| Change in Weight after Exposure in Water D 471 158°f, 166 h, one side only, max. (%) | 0.0, +6.0 | 0.0, +3.7 |
| Factory Seam Strength, N (lbf) ASTM D 751 Grab Method | 1955 (440) | > Fabric Break |
| Hydrostatic Resistance, Mpa (psi) ASTM D751 | 4.1 (590) | 6.2 (900) |
| Static Puncture Resistance ASTM D 5602 (99 lbf) | pass | pass |
| Dynamic Puncture Resistance (J) ASTM D 5635 | 10 | > 30 |



For more information on FiberTite Systems and accessories please call:
Seaman Corporation (800) 927-8578
International (330) 262-1111
www.fibertite.com

INTELLIGENT ROOFING SOLUTIONS

FiberTite® is a registered trademark of Seaman Corporation.



Subject to the conditions of Approval for a roof covering when installed as described in the current edition of the Approval Guide.



As to an external fire exposure only. See UL directory of products certified for Canada and UL roofing materials and systems directory 34KL, 48P0, 97P9.



DC196



CRRC



CHEMICAL FABRICS & FILM ASSOCIATION, INC.



ESR-1456



These specifications are current as of the date of printing. Revisions or additions may be issued periodically. For a listing, presentation, and download of the most recent data, visit:

www.fibertite.com/document-library/product-data-sheets

60 mil FiberTite-XT

Product Data

APPLICATION

8155 FiberTite-XT Roofing Systems carry extensive FM Global and Underwriters Laboratories approvals. 8155 FiberTite-XT Roofing Systems can be installed by mechanically fastening the membrane with FiberTite Magnum Fasteners and Stress Plates or adhering the membrane in FTR 190e bonding adhesive to pre-approved substrates. 8155 FiberTite-XT can also be installed in typical ballast configurations using conventional stone or paver ballast.

For specific installation recommendations and requirements, please consult the most current versions of Seaman Corporation's Guide Specifications for the Installation of FiberTite Roofing Systems.

PHYSICAL PROPERTIES (cont.)

| ASTM D6754-15 | Minimum Requirements | 8155 Typical | | |
|---|-----------------------------------|-------------------|----------------------|---------------------|
| Accelerated Weathering <i>Practice G 155 / xenon</i> | 5000hr | >10000hr | | |
| cracking (7x magnification) | none | none | | |
| crazing (7x magnification) | none | none | | |
| Accelerated Weathering <i>Practice G 154 / UVA</i> | 5000hr | >10000hr | | |
| cracking (7x magnification) | none | none | | |
| crazing (7x magnification) | none | none | | |
| Fungi Resistance <i>Practice G 21, 28 days</i> | Sustained Growth Discoloration | no growth none | no growth none | |
| Abrasion Test, cycles <i>D 3389 H-18 wheel / 1,000 g load</i> | 1,500 | 2,000+ | | |
| Additional Physical Properties | | | | |
| Tensile Strength (psi) <i>ASTM D882</i> | > 9500 | | | |
| Breaking Strength (lbs) <i>ASTM D751, Grab Method</i> | 600 | | | |
| Puncture Resistance (lbs) <i>ASTM D751, Bursting Strength</i> | 700 | | | |
| Water Vapor Transmission <i>ASTM E96 proc. A (gm/m²/24hrs)</i> | 1.3 | | | |
| Shore A Hardness <i>ASTM D2240</i> | 87 | | | |
| Flame Resistance <i>MIL-C-20696C / Type II Class 2</i> | pass | | | |
| Oil Resistance, MIL-C-20696C <i>No swelling, cracking or leaking</i> | none | | | |
| Hydrocarbon Resistance, MIL-C-20696C <i>No swelling, cracking or leaking</i> | none | | | |
| High Temperature Dead Load <i>ASTM D751 (50 lbs, 160°F, 4 hrs)</i> | pass | | | |
| Energy Attributes | DC196 Off White | DC6 White | DC671 CR Gray | DC667 CR Tan |
| Initial Solar Reflectance <i>ASTM C1549</i> | 0.83 | 0.87 | 0.69 | 0.72 |
| Solar Reflectance (3 yr aged) <i>ASTM C1549</i> | 0.66 | 0.71 | .61 | .63 |
| Initial Thermal Emittance <i>ASTM C1371</i> | 0.85 | 0.85 | 0.89 | 0.88 |
| Thermal Emittance (3 yr aged) <i>ASTM C1371</i> | 0.74 | 0.84 | .89 | .89 |
| Solar Reflective Index (SRI) <i>ASTM E1980</i> | 104 | 110 | 84 | 88 |
| Solar Reflective Index (SRI) (3 yr aged) <i>ASTM E1980</i> | 76 | 86 | 73 | 76 |
| Energy Star | YES | YES | YES | YES |
| LEED v4 - Heat Island Reduction <i>SS Credit</i> | 1 Credit | 1 Credit | 1 Credit | 1 Credit |



**INTELLIGENT
ROOFING SOLUTIONS**