


COMPLEMENTARY PRODUCTS



Geotextile
Membrane



HI-FLEX EPDM
Membrane

PHYSICAL PROPERTIES

THD (type 3) Expanded Polystyrene

Thermal Resistance (ASTM C518 C177) Thickness of 25 mm (1")	RSI-0.74 R-4.2
Vapour Permeability (ASTM E96) Thickness of 25 mm (1")	2.25 perm 130 ng/Pa·s·m ²
Compressive Strength (ASTM D1621) Thickness of 38 mm (1 1/2")	210 kPa 30.6 lbs/in ²
Flexural Strength (ASTM C518 C203) Thickness of 38 mm (1 1/2")	300 kPa 43.71 lbs/in ²
Water Absorption (ASTM D2842) Thickness of 38 mm (1 1/2")	2%
Density (ASTM D1621)	32.03 kg/m³ 2 lbs/ft ³
Limiting Oxygen Index (ULC S-701) % minimum	24%
Dimension Stability (ASTM D2126) % max. of linear change	1.5%

DESCRIPTION

Grooved expanded polystyrene insulation, shipped on all four sides, designed to facilitate drainage of water in inverted roof systems.

CERTIFICATIONS



PS 100%



LEED

- Meets ASTM C 1338 Standard, R04-690 report; test methods to determine mold resistance.

INSTALLATION

1. The installation of the insulation is done in total independence.
2. Place the panels in a single layer and in close contact, in parallel rows and without deformation or empty space.

ADVANTAGES

Low Water Absorption

The closed cell walls are waterproof and as such, water can only penetrate in channels located between polystyrene cells that are held together.

High-Dimensional Stability

According to industry standards, EPS is one of the leaders in terms of size maintenance. This helps the system to remain fully waterproof at all times.

Captive Gas; 98% Air and 2% Plastic

This formula has been used for more than 50 years. It does not contain any VOC, CFC's, HCFC's, Formaldehyde or any gas that can impact the ozone layer. Furthermore, this provides the product with premium features including its light weight and the maintenance of R-Value.

Environmentally friendly

EPS is 100% recyclable and contains 10% recycled materials. Produced locally, the distance between the plant and site is often shorter than other products of the industry.

Mildewproofing

EPS contains materials that do not support the growth of bacteria such as spores and mushrooms.

Meets High Standards

Helps to reach Novoclimat (in Quebec if applicable), EnergyStar (Ontario and the Maritimes) and R-2000 (Canada) insulation levels.

Continued on back

IZODRAIN

TYPE THD

GROOVED EXPANDED POLYSTYRENE INSULATION BOARD

DIMENSIONS

Width x Length*	1,219 mm x 1,219 mm 48" x 48"
Thickness of Straight Edge	51 mm x 305 mm 2" x 12"
Thickness of Shiplapped Edge	51 mm x 305 mm 2" x 12"
Shiplap	13 mm or 16 mm 1/2" x 5/8"
Nb of Grooves per Side	5
Width of the Grooves	25 mm 1"
Depth of the Grooves	19 mm 0.75"
Number of Panels by Bundle	Varies according to the thickness

*Other dimensions available upon request.

