



# SWS\*

## Silicone Weatherproofing Sealant

### Product Description

SWS weatherproofing sealant is a single-component, neutral cure silicone, which is an excellent candidate for use in new or remedial weathersealing applications. SWS exhibits negligible change in physical properties after weathering and upon cure, becomes a low-modulus, formed-in-place durable rubber building joint & glazing sealant.

### Key Features and Typical Benefits

#### Performance

- **Silicone Durability**—Cured silicone rubber exhibits excellent long-term resistance to natural weathering, including: ultraviolet radiation, high and low temperatures and rain and snow, with little change in elasticity.
- **High Performance**—SWS offers the durability of a true silicone sealant but at an economical price level similar to lesser-performing sealant types.
- **±50% Movement Capacity**—Can accommodate 50% movement in both extension and compression and has excellent recovery after cycling.
- **Primerless Adhesion**—To many substrates and finishes. May be considered a candidate for use with the following materials: glass, polycarbonate, vinyl, plastics, wood, painted & anodized aluminum, brick, terra-cotta, ceramic and porcelain materials, concrete and natural stones. Some finishes or substrates may require a primer.

#### Application

- **Good Workability**—Temperature stable paste which is easily gunned and tooled under hot and cold conditions.
- **Extended Work Life**—Designed to allow sufficient time for placement and tooling before skinning.

### Potential Applications

SWS is an excellent candidate to consider:

- As a weatherproofing material when sealing between dissimilar or similar materials in either new or remedial glazing and sealing applications, window perimeters and punched openings.
- For sealing to precast concrete, site cast concrete and tilt-up concrete joints.
- As a general purpose sealant for seams and curtainwall frames, screw heads, back pans, etc.

#### SWS is not:

- For use in structural glazing applications.
- For use in food contact applications.
- For use in applications where the product will be in continuous contact with water.
- Paintable (except when using SilShield\* 2400 or Optic\* 2401 silicone elastomeric coating).
- For use on wet, damp, frozen or contaminated surfaces.


### Packaging

SWS is available in 10.1 fl. oz. (299 ml) plastic caulking cartridges and 20 fl. oz. (591 ml) foil sausage packs.



### Colors

SWS is available in standard colors:



SWS02  
White



SWS03  
Black



SWS04  
Limestone



SWS08  
Light Grey



SWS09  
Aluminum



SWS12  
Special Grey



SWS13  
Beige



SWS14  
Dolphin Grey



SWS15  
Stone Grey



SWS16  
Slate Grey



SWS17  
Sandalwood



SWS18  
Charcoal



SWS19  
Redwood  
Tan



SWS20  
Precast  
White



SWS21  
Monument  
Stone



SWS46  
Champagne



SWS97  
Bronze

### Typical Physical Properties

Typical property values of SWS as supplied and cured are set forth in the tables below. Typical product data values should not be used as specifications. Assistance with specifications is available by contacting Momentive Performance Materials.

#### Typical Properties – Supplied

Property	Value <sup>(1)</sup>	Test Method
Consistency	Paste	
Polymer	100% Silicone	
VOC	1.20 wt.%	WPSTM C1454
Tooling Time	30-40 minutes	
Tack Free Time (@ 72°F/22°C, 50% RH)	3-4 hours	ASTM C679
Sag/Slump	0.1" max (2.5 mm)	ASTM D2202

#### Typical Properties – Cured<sup>(1)</sup>

Property	Value <sup>(1)</sup>	Test Method
Hardness, Type A Indenter	22	ASTM D2240
Tensile at 25%	19.3 psi (0.13 MPa)	ASTM C1135
Tensile at 50%	30.6 psi (0.21 MPa)	ASTM C1135
Peel Strength (21-day cure @ 72°F/22°C 50% RH)	>45 pli	ASTM C794
Movement Capability	±50%	ASTM C719
Service Temperature Range (after cure)	-55°F to +250°F (-48°C to 121°C)	
Application Temperature Range	+40°F to +122°F (4°C to 50°C)	
Cure Time (1/4" or 6 mm deep section) @ 72°F/22°C 50% RH	2-3 days	
Full Cure (most common bead sizes)	7-10 days	

(1) Typical properties are average data and are not to be used as or to develop specifications.

### Installation

Sealants may not adhere or maintain long-term adhesion to substrates if the surface is not prepared and cleaned properly before sealant application. *In all cases the applicator must confirm the acceptability of each sealant-substrate combination with a site adhesion test prior to proceeding with project installation.* A GE sealant primer may be selected to enhance sealant bonding on some difficult to adhere to substrates. MPM can provide information and suggestions to user upon request.

### Surface Preparation

#### Glass, Metals Paints, Smooth Surfaces, etc.

- Smooth surfaces can be wiped clean using a rag dampened with a cleaning solvent (Isopropyl Alcohol is typically useful). Proceed by cleaning the surfaces using a rag wetted with solvent and immediately use a second clean rag to wipe the wet solvent from the surface before it evaporates. Repeat this procedure as necessary until no contaminants are visible on the second cleaning rag.
- Rough surfaces such as concrete, brick and masonry can be cleaned by wire brush, mechanical abrading, grinding or a combination of these methods to provide a stable clean surface for sealant application. Secondly, follow this with an air blow or brush (soft-bristled) to remove dust.
- All surfaces that are to receive sealant must be clean, dry and free of contaminants (such as moisture/frost, oils, concrete form release agents, old sealants, asphalt and other surface treatments, etc.) to allow for optimal adhesion.



### Masking

Masking tape can be, if desired, to ensure a neat job and to protect adjoining surfaces from over-application of sealant. Masking tape should be removed immediately after tooling the sealant and before the sealant begins to skin over (tooling time).

### Joint Designs and Dimensions

**Joint Movement** - All moving joints should be designed so as not to allow three-sided adhesion of the sealant to occur. Three-sided adhesion hinders the ability of the sealant to extend and compress freely as desired and can lead to early joint failure (reference ASTM C1193 *Standard Guide for Use of Joint Sealants*).

**Joint Width** - Designed joint width must be at least 2X the total anticipated joint movement. A minimum width of 1/4" (6.35mm) is recommended in all applications and the recommended sealant profile is an hourglass shape with the depth of the sealant over the crown of the backer rod between 1/8" (3.175mm) and 3/8" (9.525mm).

### Applicable Standards

SWS meets or exceeds the requirements of the following specifications: **American Society for Testing & Materials International.**

- C920 Standard Specification for Elastomeric Joint Sealants; Type S, Grade NS, Class 50, Use A, G, M, O.

### Technical Services

Additional technical information, literature, laboratory testing and application engineering may be available upon request from MPM. Any technical advice furnished by MPM or any representative of MPM concerning any use or application of any MPM product is believed to be reliable but MPM makes no warranty, expressed or implied, of suitability for use in any application for which such advice is furnished.

### Limitations


Customers must evaluate MPM products and make their own determination as to fitness of use in their particular applications.

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Safety Data Sheets are available at [www.siliconeforbuilding.com](http://www.siliconeforbuilding.com) or, upon request, from any MPM representative. Use of other materials in conjunction with MPM sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.





### Customer Service Centers

<b>Americas</b>	+1 800 295 2392 +1 704 805 6946 Email: commercial.services@momentive.com
<b>Europe, Middle East, Africa, and India</b>	+00 800 4321 1000 +40 212 044229 Email: 4information.eu@momentive.com
<b>Asia Pacific</b>	<b>Japan</b> 0120 975 400 +81 276 20 6182  <b>China</b> +800 820 0202 +86 21 3860 4892  <b>All APAC</b> +60 3 9206 1543  Email: 4information.ap@momentive.com
<b>Visit us at <a href="http://www.siliconeforbuilding.com">www.siliconeforbuilding.com</a></b>	

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

GE is a registered trademark of General Electric Company and is used under license by Momentive Performance Materials Inc.

SWS, SilShield and Optic are trademarks of Momentive Performance Materials Inc.

Copyright 2008-2018 Momentive Performance Materials Inc. All rights reserved.

**[siliconeforbuilding.com](http://siliconeforbuilding.com)**